

TECHNICAL SPECIFICATION SHEET

Ultra Low Density Cast Hand Stretch 23um

Revision Date: August 01, 2016

Colour	Clear
Availability	Asia Pacific, Europe, North America
Description	23*500*4.23kg 23°C, 50% Humidity
Application	Cast Film Cast Stretch Film General Packaging Personal Care Packaging Films

Properties	Test Condition	Test Method	Unit	Typical Value
Tensile Strength	23°C, 50% moist	GB13022	Mpa	38.6 21
Tensile Elongation, @ Break	23°C, 50% moist	GB13022	%	456 704
Haze	23°C, 50% moist	GB2410	%	1.6
Self-Adhesion	23°C, 50% moist	Q/320684DTT01	N/cm2	0.9
Thickness	23°C, 50% moist	GB/T6672	um	23
Width	23°C, 50% moist	GB/T6673	mm	498
Weight	23°C, 50% moist		kg	4.23
Core Length	23°C, 50% moist	Q/320684DTT01	mm	513
Core Inner Diameter	23°C, 50% moist	Q/320684DTT01	mm	75.5

Note:

The information contained herein, including, but not limited to, data, statements and typical values, are given in good faith. Pro-Pac Packaging (Aust) Pty Ltd makes no warranty or guarantee, expressed or implied,

- i) that the result described herein will be obtained under end use conditions, or
- ii) as to the effectiveness or safety of any design incorporating Pro-Pac Packaging material, products, recommendations or advice.

Further, any information contained herein shall not be construed as part of a legally binding offer. Especially, the typical values should be regarded as reference values only and not as binding minimum values. Each user bears full responsibility for making its own determination as to the suitability of Pro-Pac Packaging materials, products, recommendations, or advice for its own particular use. Each user must identify and perform all tests and analyses necessary to assure that its finished parts incorporating Pro-Pac Packaging material or products will be safe and suitable for use under end use conditions. The data contained herein can be changed without notice as a result of the quality improvement of the products.